FIBERFRAX DURAFELT Z

Fiberfrax Durafelt products are manufactured from Fiberfrax refractory ceramic fibres, blended with specially selected organic binders to give flexible felts with exceptional characteristics.

Our advanced felting process ensures a lightweight, high strength product enhanced by low thermal conductivity and exceptional handling characteristics. The various blends of refractory fibres used in the manufacturing process, provides a comprehensive range of felts with operating temperature limits up to 1500°C. Fiberfrax Durafelt products are available in a wide range of sizes and thicknesses.



General Characteristics

S

Ζ

Ο

ഗ

ш

Ľ

4

Ľ

ш

ך ע

Ш Н

Т

വ

Т

С К С

A E A Fiberfrax Durafelt products have these outstanding characteristics:

- High temperature stability
- Low thermal conductivity
- High resiliency
- Lightweight
- Excellent flexibility
- Easy to wrap, cut and shape

Typical Applications

- Flexible high temperature gaskets and seals
- Ingot mould liners
- Molten metal transfer systems (back-up insulation)
- Expansion joints

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

Typical Product Parameters

Typical Chemical Analysis (fibre wt. %)				
SiO ₂	52,0 - 56,0			
Al ₂ O ₃	28,0 - 32,0			
ZrO ₂	14,0 - 18,0			
Alkalis	< 0,25			

Physical Properties

Colour	White/Beige	
Melting Point	1740°C	
Product Density	200 – 300 kg/m ³	
Tensile Strength	> 50 kPa	
Classification Temp.	1400 °C	
Loss on ignition	< 10,0 wt. %	

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750 Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0 Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78 Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0



www.insulcon.com

Form: A1-007 Effective:03012022/ES Supersedes: 12082014/FI/ka All Rights Reserved LD: UNOV12

Thermal Conductivity (W/mK) @ Mean Temp.

600°C	-
800°C	0,15
1000°C	0,21
1200°C	0,29
1400°C	-

Permanent Linear Shrinkage (%) 24 Hour Soak

1250°C	_
1400°C	< 4,0
1500°C	-

*Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact us. Where appropriate Physical Properties data measured according to EN 1094-1.

Handling Information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Availability

Thickness (mm)	Roll Le	Roll Length (m)		Sheets per Carton
	610	1220		1250 x 1000
3	30	90	√*	32
6	15	45	\checkmark	16
9	10	30	\checkmark	10
12	10	10	\checkmark	8
18			\checkmark	5
25			\checkmark	4
30				3

*Also available in rolls of 1000mm x 12m and 1000mm x 25m.

Other thicknesses / sizes may be available on request subject to minimum order requirements

ທ Z

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750 Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0 Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78 Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0



eader in high temperature solutions

Form: A1-007 Effective:03012022/ES Supersedes: 12082014/FI/ka All Rights Reserved LD: UNOV12

TECHNICAL DATASHE