

FYREWAP LT BLANKET

Description

FyreWrap® LT Blanket is a new lightweight, & flexible high temperature insulation blanket manufactured from Insulfrax low biopersistence fibres and is specifically designed for passive fire protection applications.

With its enhanced fibre properties, **FyreWrap® LT Blanket** offers significant weight savings when compared with both traditional AES wool blankets and more particularly mineral wool based products.

The modified fibre characteristics also give **FyreWrap® LT Blankets** Improved handling characteristics. Thin, lightweight systems, combined with a flexible and easy to install form result in lower installation costs and significant weight savings.

The fibres are totally inorganic and **FyreWrap LT Blanket** contains no binder, no smoke or fumes are generated when exposed heat.

Fire Protection properties

- Non Combustible to IMO FTP code Part 1
- Classified A1 to EN 13501-1

Typical applications

FyreWrap LT Blanket is suitable for use in a wide variety of passive fire protection applications including:

- Marine deck and bulkhead insulation in all types of craft
- Hydrocarbon and jet fire protection of vessels and pipes
- Bulkhead & deck insulation for offshore oil platforms & FPSO's
- Cable tray fire protection
- Ductwork fire protection
- Infill of fire doors and lightweight cladding panels


Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

TYPICAL PRODUCT PARAMETERS

Ambient Insulation Performance

Blanket Thickness	R Value	U Value
25 mm	0.78	1.28
40 mm	1.25	0.80
45 mm	1.41	0.71
50 mm	1.56	0.64
55 mm	1.72	0.58

Based on thermal conductivity of FyreWrap LT Blanket 64 kg/m³ density measured to BS EN 12667 at 10°C of 0.0320 W/mK.



BV 2690

FYREWRAF LT BLANKET

For blanket densities above 64 kg/m³ the same values may be used.

Acoustic Insulation Performance

Sound Absorption Coefficient

Frequency Hz	50 mm x 70 kg/m ³	50 mm x 96 kg/m ³
125	0.47	0.26
250	1.05	0.94
500	1.09	1.03
1000	1.09	1.03
2000	1.12	1.09
4000	1.12	1.14
5000	1.18	1.09

Noise Reduction

Coefficient	1.10	1.00
-------------	------	------

Test method BS EN ISO 354:2003. Foil facing will reduce the sound absorption characteristics.

Thermal Conductivity (W/mK)

Mean Temp. (°C)	64kg/m ³	96kg/m ³	128kg/m ³
200	0.06	0.06	0.05
400	0.11	0.09	0.08
600	0.17	0.14	0.12
800	0.26	0.20	0.18
1000	0.38	0.29	0.25

Thermal Conductivity measured in accordance with ASTM C-201.

Blanket Facings

FyreWrap LT Blanket can be supplied faced with choice of facing. The following grades are available:

FyreWrap LTF Blanket with 30µm foil on one face.

FyreWrap LTFR Blanket with 30µm foil & glass fibre mesh reinforcement on one face.

FyreWrap LTG Blanket with glass fibre cloth on one face.

FyreWrap LTFE Blanket is fully encapsulated in a 200µm reinforced aluminium composite scrim.

FyreWrap LTF, LTFR & LTG blankets are available with the covering on both top and bottom surfaces of the blanket and are designated LTF2, LTFR2, and LTG2 respectively.

FYREWRAF LT BLANKET

Availability

Standard Roll Sizes

Thickness (mm)	Roll length (m)	Standard Densities kg/m ³
25	7.32	64, 96, 128
35	5.0	70
38	5.0	96, 128
40	5.0	70
45	5.0	64
50	3.66	64, 70, 96, 128
55	3.66	64, 70

Non-standard combinations may be available upon request subject to minimum)

Handling information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750
Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0
Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78
Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0

INSULCON

LEADER IN HIGH TEMPERATURE SOLUTIONS
www.insulcon.com

Form: A1-252
Effective 03012022/ES/ka
supersedes: 24062021/ES/ka
All rights Reserved
LD: U170611